


TE - Premium General Purpose Industrial

BIAXIALLY ORIENTED POLYPROPYLENE FILM
NON HEAT-SEALABLE

AMTOPP BOPP FILMS



Characteristics

- Non Heat-Sealable
- High Energy Flame Treated for excellent ink adhesion and adhesive and extrusion lamination bonds
- Flame Treated skin formulated for enhanced bonds
- Superior Optical Properties
- Excellent Flatness
- Very Good Stiffness

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES				
			TE18	TE25	TE30	TE40	TE50
THICKNESS	AmTopp	mil (μm)	0.70 (18)	0.97 (25)	1.19 (30)	1.56 (40)	1.96 (50)
YIELD	AmTopp	in ² /lb (m ² /kg)	43,400 (61.9)	31,400 (44.6)	25,700 (36.5)	19,600 (27.9)	15,600 (22.2)
TENSILE STRENGTH (MD)	ASTM D 882	lb/in ² (kg/cm ²)	20,000 (1,400)				
TENSILE STRENGTH (TD)	ASTM D 882	lb/in ² (kg/cm ²)	37,000 (2,600)				
ELONGATION AT BREAK (MD)	ASTM D 882	%	180				
ELONGATION AT BREAK (TD)	ASTM D 882	%	60				
HAZE	ASTM D 1003	%	2 - 3				
GLOSS (45 DEG)	ASTM D 2457	G.U.	85				
DIMENSIONAL STABILITY (MD)	266 °F, 5min (130° C, 5 min)	%	<5				
DIMENSIONAL STABILITY (TD)	266 °F, 5min (130° C, 5 min)	%	<3				
SURFACE ENERGY (High Energy Flame Side)	ASTM D 2578	dyne/cm	40				
SURFACE ENERGY (Corona Side if two side treated)	ASTM D 2578	dyne/cm	36				

Rev. January 2014

Applications

- In-line printed/coated pressure sensitive tape
- Specialty industrial applications requiring strong ink and coating adhesion

The above properties and results obtained refer to the average values of laboratory testing carried out on sample AmTopp product. AmTopp does not guarantee testing accuracy and makes no guarantee of product performance, safety or suitability, either expressed or implied, when used alone or in combination with other products. AmTopp strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. AmTopp assumes no responsibility for any damage or injury sustained as a result of the use of its products.