


CK - Metallizable Base (Superior Seal Strength)



Key Performance Characteristics:

Metallizable base film with very wide seal range and superior seal strength

Applications:

In house or toll metallizing for heat sealable snack laminations that require superior seal strength

Technical Data

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES	
			CK25	CK35
THICKNESS	Internal	mil (μm)	0.97 (25)	1.37 (35)
YIELD	Internal	in ² /lb (m ² /kg)	31,500 (44.8)	22,200 (31.6)
HEAT SEAL INITIATION (untreated side)	1/2 sec, 30 PSI	°F / (°C)	194/ (90)	
HEAT SEAL STRENGTH	1/2 sec, 30 PSI @248°F (120°C)	g/in	>1,000	
HAZE	ASTM D1003	%	4.0	
TENSILE STRENGTH (MD/TD)	ASTM D882	lb/in ² (kg/cm ²)	18,000 / 24,000 (1,265) / (1,690)	
ELONGATION AT BREAK (MD/TD)	ASTM D882	%	190 / 80	
DIMENSIONAL STABILITY (MD/TD)	266°F (130°C) 5 min	%	<5 / <3	
WATER VAPOR TRANSMISSION RATE (WVTR)	ASTM F 1249 100°F (38°C), 90% RH	g/100in ² /24h (g/m ² /24h)	0.70 (10.9)	0.50 (7.8)
OXYGEN TRANSMISSION RATE (OTR)	ASTM D 3985 72° F(22° C), 0%RH	cc/100in ² /24h (cc/m ² /24h)	200 (3,100)	150 (2,325)
SURFACE ENERGY	ASTM D2578	dyne/cm	40	

Revision Date: April 2017

The above properties and results obtained refer to the average values of laboratory testing carried out on sample Inteplast product. Inteplast does not guarantee testing accuracy and makes no guarantee of product performance, safety or suitability, either expressed or implied, when used alone or in combination with other products. Inteplast strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Inteplast assumes no responsibility for any damage or injury sustained as a result of the use of its products.