


# HHD - Matte Heat Sealable (Moderate COF)



### Key Performance Characteristics:

Matte finish, one side sealable, one side treated, moderate COF

### Applications:

Outer web of laminations for VFFS packaging using overlap sealing

## Technical Data

PROPERTIES	TEST METHOD	UNITS	TYPICAL VALUES	
			HHD18	HHD25
THICKNESS	Internal	mil ( $\mu\text{m}$ )	0.69 (18)	0.97 (25)
YIELD	Internal	in <sup>2</sup> /lb (m <sup>2</sup> /kg)	44,000 (62.5)	31,500 (44.8)
HEAT SEAL INITIATION (matte side)	1/2 sec, 30 PSI	°F / (°C)	240 / (115)	
HAZE	ASTM D1003	%	75	
COEFFICIENT OF FRICTION (Matte side)	ASTM D1894	Dynamic	0.40	
		Static	0.50	
TENSILE STRENGTH (MD/TD)	ASTM D882	lb/in <sup>2</sup> (kg/cm <sup>2</sup> )	17,000 / 30,000 (1,200) / (2,100)	
ELONGATION AT BREAK (MD/TD)	ASTM D882	%	190 / 70	
DIMENSIONAL STABILITY (MD/TD)	266°F (130°C) 5 min	%	<5 / <3	
WATER VAPOR TRANSMISSION RATE (WVTR)	ASTM F1249 100°F (38°C), 90% RH	g/100in <sup>2</sup> /24h	0.45	0.35
		(g/m <sup>2</sup> /24h)	(7.0)	(5.4)
SURFACE ENERGY	ASTM D2578	dyne/cm	40	

Revision Date: September 2017

The above properties and results obtained refer to the average values of laboratory testing carried out on sample Inteplast product. Inteplast does not guarantee testing accuracy and makes no guarantee of product performance, safety or suitability, either expressed or implied, when used alone or in combination with other products. Inteplast strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. Inteplast assumes no responsibility for any damage or injury sustained as a result of the use of its products.