

Inteplast Group
World - Pak Division
***IntePlus*[®] Business Dept.**

TECHNICAL DATA SHEET
IntePlus[®]

Film Type: XF - BW

Property	Test Method	Unit	Film Direction	Typical Value		
Thickness	XFWI0201	GSM	--	110 ± 10%	125 ± 10%	150 ± 10%
		Mil	--	4.6 ± 10%	5.3 ± 10%	6.3 ± 10%
Tensile @ Ultimate	ASTM-D882	lb/in	MD	30	38	43
			TD	22	23	26
Elongation @ Ultimate	ASTM-D882	%	MD	450	500	550
			TD	450	500	550
Dart Impact	ASTM-D1709 (Method A)	grams	--	500	1000	1100
PP Tear	ASTM-D2582	grams	MD	8000	8800	10000
			TD	8000	10000	11000

Please note that the above information is to the best of our knowledge and is made without guarantee. These are typical property values and are intended as guides only, not as specification limits. We can not anticipate all conditions under which this information and our products, or products of other manufacturers in combination with our products may be used. Users are advised to conduct their own test and evaluation to determine the safety and suitability for their own purposes. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products.

For additional information, call 1-800-452-2117, extension 8058.

Issued Date: 12/17/07