

Inteplast Group
World-Pak Division
***IntePlus*[®] Business Dept.**

TECHNICAL DATA SHEET
IntePlus[®]

Film Type: XF - US

Property	Test Method	Unit	Film Direction	Typical Value		
Thickness	XFWI0201	GSM	--	90 ± 10%	110 ± 10%	125 ± 10%
		Mil	--	3.8 ± 10%	4.6 ± 10%	5.3 ± 10%
Tensile @ Ultimate	ASTM-D882	lb/in	MD	20	24	26
			TD	18	20	23
Elongation @ Ultimate	ASTM-D882	%	MD	650	650	700
			TD	650	650	650
Dart Impact	ASTM-D1709 (Method A)	grams	--	600	650	700
PP Tear	ASTM-D2582	grams	MD	8,000	8,500	9,000
			TD	8,000	8,500	9,000
Beach Puncture	ASTM-D781	in-lb	MD	> 48	> 48	> 48
			TD	> 48	> 48	> 48
MVTR	ASTM E96(B) (Method B)	US Perm Perm	--	0.111	0.091	0.080
Fire Rating	ASTM E84	Class	--	A	A	A

Please note that the above information is to the best of our knowledge and is made without guarantee. These are typical property values and are intended as guides only, not as specification limits. We can not anticipate all conditions under which this information and our products, or products of other manufacturers in combination with our products may be used. Users are advised to conduct their own test and evaluation to determine the safety and suitability for their own purposes. We accept no responsibility for results obtained by the application of the information or the safety and suitability of our products.

For additional information, call 1-800-452-2117, extension 8058.

Issued Date: 12/17/07